

This is the peer reviewed version of the following article:

Marinković S., Carević V. and Dragaš J. “The role of service life in Life Cycle Assessment of concrete structures”, *Journal of Cleaner Production*, vol. 290, pn. 125610, March 2021.

<https://doi.org/10.1016/j.jclepro.2020.125610>

1 **The role of service life in Life Cycle Assessment of concrete structures**

2

3 Snežana Marinković<sup>1\*</sup>, Vedran Carević<sup>1</sup>, Jelena Dragaš<sup>1</sup>

4

5 <sup>1\*</sup> University of Belgrade, Faculty of Civil Engineering, Bulevar kralja Aleksandra 73, 11000

6 Belgrade, Serbia;

7

8 \*Corresponding author Tel. 0113218547

9 E-mail address: [sneska@imk.grf.bg.ac.rs](mailto:sneska@imk.grf.bg.ac.rs)

10 Postal address: Faculty of Civil Engineering, Bulevar kralja Aleksandra 73, 11000 Belgrade,

11 Serbia

12

13 Vedran Carević: [vedran@imk.grf.bg.ac.rs](mailto:vedran@imk.grf.bg.ac.rs)

14 Jelena Dragaš: [jelenad@imk.grf.bg.ac.rs](mailto:jelenad@imk.grf.bg.ac.rs)

15

16

17

18

19

20

21

22

23

24

25

1 Word count:

2 **Abstract**

3 In comparative Life Cycle Assessment (LCA) of concrete structures it is of crucial importance  
4 to provide the functional equivalence of compared alternatives. Most commonly, the  
5 comparison is performed between the structures made of conventional and green concrete  
6 mixtures. Since they have different mechanical and durability properties, corresponding  
7 structures have different strength and service life. While resolving this problem, two  
8 approaches are generally possible: either correction of the functional unit volume or correction  
9 of the calculated environmental impacts with compressive strength and duration of service  
10 life, if functional unit has the same volume. In this work, in order to assess the effect of  
11 service life modeling in LCA, both approaches were tested. As a demonstration, comparison  
12 of both slabs and beams made of conventional and high volume fly ash concrete exposed to  
13 carbonation was carried out. LCA was performed for 94 different mixtures from reported  
14 experimental research and calculated environmental impacts (**climate change, acidification,**  
15 **eutrophication, photochemical-oxidant creation, and abiotic depletion of fossil fuels**) for  
16 both approaches were compared. Results showed that different modeling of service life in  
17 LCA can result in totally different, even opposite conclusions. With slightly larger volume of  
18 functional unit (**7%-20%**), all normalized environmental impacts of high volume fly ash  
19 concrete structural members were lower for an order of magnitude (**6 - 7 times**) compared to  
20 those obtained on the basis of the same volume approach. Therefore, drawing conclusions  
21 only on the basis of service life modeling with the same volume approach may be misleading.  
22 The proper choice of the best alternative should be based on the integrated assessment which  
23 includes structural, environmental and cost assessment of the structure as a whole.

24

25 **Keywords:** concrete structure, service life, LCA, environmental impact, integrated assessment

## 1 **1. Introduction**

2 It is well recognized today that human activities cause major environmental impacts. Among  
3 many others, the construction industry places a large burden on the environment: huge  
4 consumption of natural resources, especially non-renewable fossil fuels, large emissions of  
5 substances that pollute the air, soil, and water, as well as the generation of substantial amounts  
6 of inert and toxic waste.

7 More specifically, the concrete industry plays a leading role in this process: concrete  
8 production is not especially harmful per unit of concrete; however, the global production and  
9 utilization of concrete is very high – roughly 25 billion tons of concrete are produced globally  
10 each year, or over 3.8 tons per person per year (WBCSD, 2009), only second to water in  
11 mankind's consumption. In developed countries, structural concrete (concrete utilized in  
12 reinforced concrete structures) constitutes over 50% of all concrete, and developing countries  
13 will follow this trend (UN Environment, 2018). The cement industry causes approximately  
14 10% of the overall anthropogenic CO<sub>2</sub> emissions (UN Environment, 2018) in the world – more  
15 than 50% of the yearly CO<sub>2</sub> is related to building activities. The IEA study (IEA, 2018) found  
16 that CO<sub>2</sub> emissions in the cement industry, consistent with at least a 50% chance of limiting the  
17 average global temperature increase to 2°C by 2100, would require an overall reduction of 24%  
18 in the CO<sub>2</sub> direct emission from current levels by 2050.

19 For these reasons it is of crucial importance to find way(s) of greening the concrete industry,  
20 i.e., to decrease its impact on the environment. These efforts can be divided into three major  
21 groups: (1) recycling of construction and demolition waste as a way to reduce the amount of  
22 waste and consumption of natural resources, (2) on the material level, by introducing green  
23 concretes, and (3) on the structural level, by design for longer service life and reuse.

24 Green concretes are developed with the following aims:

1 - to reduce the natural aggregate's (NA) consumption and waste generation – for the  
2 production of these green concretes recycled concrete aggregates (RCA) are used instead of  
3 NA; they are called recycled aggregate concretes (RAC);  
4 - to reduce CO<sub>2</sub> emissions which originate mostly from cement production, namely by using a  
5 low content of cement.

6 Part of the cement is usually replaced by the so called supplementary cementitious materials  
7 (SCMs) with low embodied CO<sub>2</sub>. The most common SCMs are reactive wastes from other  
8 industries; for instance, fly ash (FA), the by-product of the electricity production in coal-  
9 burning power plants, can be used for this purpose because it has pozzolanic properties.

10 Granulated blast furnace slag (GBFS), a by-product of pig-iron production in blast furnaces, is  
11 also commonly used. Fillers, inert or weakly reactive fine particulate materials, can partially  
12 replace cement or other reactive SCMs; the most commonly used is limestone filler.

13 The cement content in concrete can also be reduced by appropriate mix design methods such  
14 as particle packing methods (Fennis and Walraven, 2012; Sunayana and Barai, 2017). These  
15 methods enable better concrete properties with a smaller amount of cement. Recently, research  
16 has focused on the possibility of replacing large parts of cement with inert fillers and super  
17 plasticizers, in combination with particle packing methods (John et al., 2018).

18 Due to the high global production of concrete, CO<sub>2</sub> mitigation strategies require material  
19 alternatives to be available in large amounts. According to a UN report (UN Environment,  
20 2018) there is not much future in replacing cement with common SCMs such as GBFS and  
21 FA, because of their limited global availability. The estimate is that quality sources of GBFS  
22 and FA will be limited globally to only about 15–25% of cement production by 2050 and are  
23 unlikely to increase. This amount is hardly enough for the production of composite cement  
24 (CEM II) (CEN, 2008) which contains up to 35% of SCMs and is highly utilized in structural  
25 concrete. For that reason, this report recommends recently developed alternative SCM systems

1 that use a combination of calcined clays and ground limestone or a combination of filler, super  
2 plasticizers, and particle packing mix design methods. Beside limestone, many other minerals  
3 can be used as fillers in concrete, so they are abundantly available everywhere.

4 However, there are regions in the world where FA availability is significantly above the global  
5 average. These are regions where most of electricity is produced in coal-fired power plants,  
6 with rapid technology change that is unlikely to occur in the near future. For instance, in  
7 Serbia, 70% of electricity is produced in such plants. The annual production of FA and bottom  
8 ash is 7 million tons, with 300 million tons of FA already deposited on an area of more than  
9 1500 ha. On the other hand, the annual production of cement in Serbia is about 2 million tons.

10 Only 3% of FA is utilized, mostly in cement production. Much larger utilization of FA is  
11 therefore urgently needed in some regions of the world. For this reason, high volume fly ash  
12 concrete (HVFAC) was developed as a concrete which contains more than 40–50% of FA in  
13 the total mass of cementitious materials. With proper mix design and quality FA, this concrete  
14 can have properties necessary for structural applications.

15 Whichever SCM, filler, aggregate type, or mix design method is used, the aim is to keep the  
16 structural performance of concrete at a desired level. Up to now extensive research was  
17 performed regarding the properties of HVFAC and RAC (see references for databases) and  
18 regarding the behavior of structural elements containing them (Ajdukiewicz and Kliszczewicz,  
19 2007; Arezoumandi and Volz, 2013; Arezoumandi et al., 2014; Dragaš et al., 2016; Ignjatović  
20 et al., 2013, 2017a; J. Pacheco et al., 2015; Knaack and Kurama, 2015; Sadati et al., 2016;  
21 Seara-Paz et al., 2018; Tošić et al., 2016, 2018; Xiao et al., 2012; Yoo et al., 2015). Although  
22 the production technologies are readily accessible and properties are well investigated, their  
23 application in structural concrete is not yet standardized (or it is allowed but with strong  
24 limitations canceling possible benefits). They are slowly entering the structural codes and, for

1 instance, the new version of Eurocode 2 (CEN, 2004) planned for 2020 introduces RAC as a  
2 viable structural concrete.

3

## 4 **2. Effect of service life on the life cycle environmental impacts of concrete structures -** 5 **choice of functional unit**

6 **A lot of research in the last decade was devoted to the environmental assessment of**  
7 **conventional and green concretes and it was, almost exclusively, performed by using Life**  
8 **Cycle Assessment (LCA) in comparative assessments (Knoeri et al., 2013; De Schepper**  
9 **et al., 2014; Celik et al., 2015; Jiménez et al., 2015; Turk et al., 2015; Teixeira et al., 2016;**  
10 **Braga et al., 2017; Marinkovic et al., 2017; Van den Heede et al., 2017; Vieira et al.,**  
11 **2018; Zhang et al., 2019). Various commercial and non-commercial LCA software, including**  
12 **Life Cycle Inventory (LCI) databases (SimaPro ([www.pre.nl](http://www.pre.nl)), Gabi ([software.com](http://www.gabi-</a></b><br/>13 <b><a href=)), Athena ([www.athenaSML.ca](http://www.athenaSML.ca)), TEAM ([www.ecobilan.com](http://www.ecobilan.com)), JEMAI**  
14 **([www.jemai.or.jp/english/index.cfm](http://www.jemai.or.jp/english/index.cfm)),) and LCI databases (Ecoinvent**  
15 **([www.pre.nl/ecoinvent](http://www.pre.nl/ecoinvent)), ELCD (<http://lca.jrc.ec.europa.eu>), BEES**  
16 **([www.nist.gov/el/economics/BEESSoftware.cfm](http://www.nist.gov/el/economics/BEESSoftware.cfm)), etc. were developed. Although the**  
17 **environmental aspect is not the only pillar of sustainability, it is the most investigated one,**  
18 **because the social aspect is hard to quantify. On the other hand, it is easy to include **the****  
19 **economic aspect (cost) in the assessment, and in fact it has always been included in the**  
20 **decision making process.**

21 **Unlike most other products, structures generally have very long service life – period of**  
22 **time in which the structure has to satisfy the required performance criteria. It ranges**  
23 **between 10 and over 100 years depending on the type of structure and its importance.**  
24 **For instance, according to European standard Eurocode 0 (CEN, 2004) design service**  
25 **life is 10 years for temporary structures, 50 years for buildings and other common**

1 structures of average importance, and 100 years or more for structures of greater  
2 importance e.g. monumental buildings, large bridges, other special or important  
3 structures.

4 Today we are able to successfully estimate service life of concrete structures for different  
5 deterioration mechanisms using probabilistic approaches such as those given in, for  
6 instance, *fib*-Bulletin 34 (2006). In design of concrete structures service life is one of the  
7 functional requirements and therefore it has to be included in LCA when defining the  
8 functional unit (FU).

9 This is especially important in LCAs where concrete structures made of conventional  
10 and green concretes are compared. Since they usually have different mechanical and  
11 durability related properties which influence service life of a structure, FU with same  
12 volume would obviously not provide the same function of compared alternatives -  
13 comparison based on the same volume approach is not justified.

14 In previous research, this problem was recognized and dealt with in several ways. Some  
15 researchers adapted the functional unit (FU) to include properties of the concrete as material  
16 (Panesar et al., 2017; Zhang et al., 2019). These authors included service life by  
17 correcting calculated impacts per unit volume with chosen concrete durability related  
18 property, such as rapid chloride permeability or chloride diffusion coefficient.

19 However, in that way the behavior of the material (plain concrete durability) and not the  
20 behavior of the structure (its service life), is taken into account. Concrete structures are  
21 made of reinforced concrete (RC) and in the most common case of steel reinforcement,  
22 basic deterioration mechanisms affecting service life are carbonation or/and chloride  
23 induced reinforcement corrosion. For these commonly investigated mechanisms the  
24 service life of RC structural member depends only on the quality of concrete in cover (in  
25 standards usually expressed through the minimum compressive strength or minimum



1 cement content) and its depth. So, there is no linear relationship between the whole  
2 chosen volume of RC member and its service life, but there is a certain, non-linear  
3 relationship between the depth of concrete cover and duration of RC member service  
4 life. And this is not the same at all since concrete cover makes only a small part of any  
5 chosen unit volume.

6 Therefore, when assessing concrete on the “material” level it is justified to apply FU based  
7 only on the material properties. Such FU can be used **only** for generic comparisons in order to  
8 evaluate the environmental potential for material substitution. Beside, such comparative LCAs  
9 should clearly state that performance of a specific application of assessed material is not taken  
10 into account.

11 **As for concrete used in RC structures, its area of application is known – it is a concrete**  
12 **structure with specific functional requirements regarding safety, serviceability and**  
13 **service life. The assessment of structural concrete cannot be performed independently of**  
14 **the structure in which the concrete is applied because service life is not the property of**  
15 **material but a function of the concrete structure.**

16 **In comparative LCA same functional requirements should be satisfied for all compared**  
17 **alternatives.** In ISO 14041 terminology (ISO, 2006), all reference flows of compared  
18 alternatives should be corrected for FU which reflects all relevant functional aspects of the  
19 concrete structure. So in comparative assessments of structural concretes, FU based on a  
20 specific concrete structure performance should be applied. **This is valid for all construction**  
21 **materials, only in the concrete case there is rather large difference between the “nature”**  
22 **of material and the “nature” of the structure.**

23 Generally, two approaches for obtaining the functional equivalence when comparing  
24 structures made of concrete with different properties are possible: either correction of the FU  
25 volume (Approach B in this work) or normalizing the calculated environmental impacts with


1 compressive strength and duration of service life if FU has the same volume (Approach A in  
2 this work). What however can lead to a very different assessment results is a fact that for the  
3 service life prediction in the case of deterioration mechanisms which cause the reinforcement  
4 corrosion, only the depth of the concrete cover in reinforced concrete (RC) member matters  
5 (as already mentioned).

6 The most applied way to model the impact of service life of concrete structures in LCA in  
7 previous research was Approach A. For instance, in Garcia-Segura et al. (2014) and Vieire et  
8 al. (2018) work, an RC column with chosen size dimensions was applied. Silva et al. (2012)  
9 performed the service life prediction for a linear member with specified length and cross  
10 section size. These assessments were based on the FU which represents the same volume of  
11 compared RC alternatives, i.e. same depth of concrete cover, resulting in different service  
12 lives of compared alternatives (Approach A in Figure 1). With this approach the functional  
13 equivalence regarding **service life** is not achieved and environmental impacts must be  
14 calculated per year of service life for proper comparison.


15 **The problem with such approach is that alternatives with poorer resistance to chosen**  
16 **deterioration mechanisms (whether conventional or green concrete) can have much**  
17 **shorter service lives and therefore significantly larger environmental impacts per year of**  
18 **service life. To avoid this situation (to be negative on green concrete performance) which**  
19 **is generated by employing Approach A solely, researchers often choose to compare**  
20 **conventional and green concretes in the exposure conditions for which green concretes**  
21 **have superior behavior (for HVFAC that would be resistance to chloride ingress). But if**  
22 **the comparison is performed for the exposure condition less favorable for green**  
23 **alternative (for HVFAC that would be carbonation resistance and carbonation is**  
24 **practically unavoidable), green concrete would be (unfairly) assessed as much less**  
25 **environmentally ‘friendly’ when service life is taken into account. In a word, commonly**

1 used Approach A can significantly overestimate the effect of durability related  
 2 properties of concrete on the LCA environmental impact results of a concrete structure.  
 3 On the other hand, there is another possible and correct approach to service life  
 4 modeling within LCA. Same service lives of compared alternatives can be obtained with  
 5 different cover depths (keeping the same member's strength), Approach B in Figure 1.  
 6 Since the depth of concrete cover is usually equal to several centimeters, this causes small  
 7 changes of volume in FU and different impact of service life on the environmental  
 8 assessment compared to Approach A. If there is a large difference between calculated  
 9 service lives of compared alternatives, results of the impact assessment using Approaches  
 10 A and B (which are both correct) would differ for an order of magnitude. To the best of  
 11 the authors knowledge this fact was not recognized in the previous research and  
 12 Approach B was not applied in assessment of concrete for structural use, i.e. concrete  
 13 structures.

**APPROACH A**



**APPROACH B**



14

15 Figure 1. Different approaches to modeling of RC slab service life in LCA

1 Following symbols are used in Figure 1:

2  $f_{cm}$  – mean concrete compressive strength

3  $\Phi$  – radius of reinforcement bar

4  $A_s$  – area of reinforcement

5  $d$  – effective depth of RC slab

6  $h$  – total height of RC slab

7  $c$  – depth of concrete cover

8 **More generally, as Approach A can be considered every approach in which the depth of**  
9 **concrete cover is assumed to have the same value for all compared concrete alternatives.**

10 **Required service life duration can be set as target and additional repair activities are**  
11 **than included in LCA for those alternatives which don't fulfill this requirement (Van**  
12 **den Heede and De Belie, 2014). Again, if there is a large difference between calculated**  
13 **service lives this can end in large number of necessary repairs and consequently larger**  
14 **impacts of alternatives with short service life.**

15 **Besides,** general conclusions on the structure's service life effect in LCA can hardly be drawn.

16 **They depend on the type (beam, slab, column...) and size of the RC member/structure**  
17 **because the participation of the concrete cover depth in the unit volume is not same for**  
18 **beam and slab for instance – the effect of service life is case-dependent.** As it was stated in

19 Purnell's work (2012) "there is no such thing as a green structural material". In fact, the most  
20 proper way in comparative assessments of RC structures is to choose the whole structure as  
21 FU (Garcez et al., 2018) while multiple structural designs are unavoidable.

22 To demonstrate this fact, this work shows how service life prediction affects the life cycle  
23 environmental impacts of different RC structural members, and how different such results can  
24 be compared to assessments based on the same volume approach or based on the material  
25 properties only. For this demonstration two different concrete mixes, conventional concrete

1 (CC) and HVFAC, and one deterioration mechanism - carbonation, were chosen. This was  
2 considered as good demonstration example since these two concrete mixtures have very  
3 different carbonation resistance. For two types of structural members, slab and beam,  
4 relationships between the chosen impact category indicators and compressive strength were  
5 derived taking into account the effect of carbonation on the service life. This was performed  
6 on the basis of experimental results from literature, using LCA and regression analyses.  
7 Impact category indicators were calculated for approximately 50 different mixtures of each  
8 concrete mix, with input LCI data chosen to represent average European production  
9 technologies.

10

### 11 **3. Databases**

12 **The uncertainty regarding the relationship between mixture proportions and**  
13 **compressive strength of concrete is rarely tested. Almost exclusively in the previous**  
14 **research only one mix design per each alternative was assessed and compared. Usually,**  
15 **three samples are tested for determining the compressive strength of the mixture and**  
16 **standard deviation is obtained. But this standard deviation (which is commonly small)**  
17 **includes the variability due to concrete technology and not due to the concrete mix**  
18 **design.**

19 **The problem is that the same compressive strength can be obtained with different**  
20 **mixture proportions, i.e. different amounts of component materials which are essential**  
21 **for the impact assessment. This is especially important for the cement amount, because it**  
22 **practically determines the main environmental impacts of concrete. The cement amount**  
23 **in the mix design is influenced not only by the strength, but also by the workability**  
24 **requirement. If workability (slump value for instance) is not equal, same compressive**  
25 **strength can be obtained with (very) different cement content, depending also on the**

1 amount of water reducing admixture. So, results of the previously published  
2 comparative LCA studies treating several specific concrete mixtures are valid only for  
3 those mixtures - if different workability requirement is set as target, different mix  
4 designs and different impacts are obtained. This fact can introduce relatively large  
5 variability of the impact results.

6 For that reason it was decided to calculate impacts on a database of concrete mixtures  
7 with broad range of strengths and workability classes collected from published  
8 experimental research. The other reason was to assess the influence of the concrete  
9 compressive strength on the impact results.

10 Experimental results on the mixture proportions and properties of CC and HVFAC were  
11 collected from available research papers, technical reports, master and doctoral theses. From  
12 all available studies only those which contained all necessary data for LCA were selected.

13 These are:

14 - type and amount of cement, FA, aggregate, and plasticizer

15 - slump and compressive strength of concrete (at 28 days)

16 Only concrete mixes with mean compressive strength  $f_{cm}$  larger than 38 MPa were chosen for  
17 the LCA analysis. This value corresponds to concrete strength class C30/37 which is the  
18 lowest strength acceptable for XC3 exposure class (concrete inside buildings with moderate or  
19 high air humidity) according to Eurocode 2 (CEN, 2004). Concrete mixes with slump values  
20 between 50 and 210 mm (classes S2, S3 and S4 according to EN 206-1 (CEN, 2011)) were  
21 selected for further analysis. Only class F fly ash according to ASTM C618 (ASTM C618,  
22 2015) was taken into account. As for plasticizer, all results with a plasticizer amount below  
23 2.5% of cement+FA mass were included in the databases. The type of curing regime can  
24 influence HVFAC properties and therefore for these mixtures the most common type was

1 selected – standard wet curing: 95–100% RH and temperature  $20\pm 2^{\circ}\text{C}$  for the first 28 days.  
2 Application of these filters led to:  
3 - 51 different mixtures in the HVFAC database (**database provided in Supplementary**) out  
4 of 440 collected results, with following ranges of parameters:  $\text{FA}/(\text{cement}+\text{FA}) = 40\text{--}60\%$ ,  
5 plasticizer 0–2.5% of the cement+FA mass and mean compressive strength at 28-days 38–67  
6 MPa.  
7 As for CC, the results were compiled of control concrete mixes from experimental campaigns  
8 which were used to obtain the HVFAC results (**database provided in Supplementary**). It  
9 contains 43 different mixes with following ranges of parameters: plasticizer 0–2.5% of the  
10 cement mass and mean compressive strength at 28 days 38–66 MPa.  
11 In selected concrete mixes, FA specific gravity ranges from  $2075 \text{ kg/m}^3$  to  $2750 \text{ kg/m}^3$ . All  
12 compressive strength results were recalculated for a 15 x 30 cm cylinder, as per Eurocode 2  
13 (CEN, 2004).

14

#### 15 **4. Modeling of carbonation resistance**

##### 16 **4.1 Carbonation depth model**

17 Carbonation is one of the most important depassivation processes. It represents the process of  
18 cement matrix neutralization which destroys the chemical protection of reinforcement (thin  
19 oxide layer produced in the hydration process). A good reinforcement protection can be  
20 achieved with adequate concrete quality and cover depth, depending on the exposure  
21 conditions. The expected carbonation depth in natural conditions directly influences the  
22 concrete cover depth required for the design service life.

23 There are several ways to predict the carbonation depth over time (natural carbonation test, a  
24 wide range of prediction models), but the probabilistic approach suggested in *fib*-Bulletin 34

1 (2006) is the most widely used. Service life is defined through limit state function for  
 2 carbonation induced reinforcement depassivation:

$$3 \quad g(c, x_c(t)) = c - x_c(t) = c - \sqrt{2 \cdot k_e \cdot k_c \cdot (k_t \cdot R_{ACC}^{-1} + \varepsilon_t) \cdot C_s \cdot t \cdot W(t)} \quad (1)$$

4 where,

5  $c$  concrete cover (mm),

6  $x_c(t)$  carbonation depth at the time  $t$  (mm),

7  $k_e$  environmental function (-),

8  $k_c$  execution transfer parameter (-),

9  $k_t$  regression parameter (-),

10  $\varepsilon_t$  error term ((mm<sup>2</sup>/year)/(kg/m<sup>3</sup>)),

11  $R_{ACC}^{-1}$  inverse effective carbonation resistance of concrete ((mm<sup>2</sup>/year)/(kg/m<sup>3</sup>)),

12  $C_s$  CO<sub>2</sub> concentration (kg/m<sup>3</sup>),

13  $W(t)$  weather function (-).

14 For carbonation depth calculation, *fib*-Bulletin 34 (2006) model takes into account the macro-  
 15 climate conditions, curing conditions and concrete properties. The impact of environmental  
 16 conditions is represented by two parameters:  $k_e$  representing the influence of relative humidity  
 17 and  $W(t)$  representing the influence of atmospheric precipitation. Taking into account that in  
 18 this study the indoor concrete members were considered, the value of the parameter  $W(t)$  was  
 19 adopted as 1. The environmental function parameter ( $k_e$ ) is defined as:

$$20 \quad k_e = \left( \frac{1 - (RH_{real} / 100)^{f_c}}{1 - (RH_{ref} / 100)^{f_c}} \right)^{g_c} \quad (2)$$

21 where,

22  $RH_{real}$  environment relative humidity (%),

23  $RH_{ref}$  referent relative humidity (%),



1  $f_c$  exponent (-),

2  $g_c$  exponent (-).

3 Execution transfer parameter ( $k_c$ ) takes into account concrete curing conditions:

$$4 \quad k_{cur} = \left( \frac{t_c}{7} \right)^{b_c} \quad (3)$$

5 where,

6  $t_c$  period of curing (days),

7  $b_c$  regression exponent (-).

8 **The curing period ( $t_c$ ) of 7 days was adopted because it is assumed that this is the**  
9 **standard time of curing on site, as well as the time defined in *fib*-Bulletin 34 (2006)**  
10 **required for the accelerated carbonation test.**

11 Parameters  $k_t$  and  $\varepsilon_t$  represent the relationship between natural and accelerated carbonation  
12 resistance and they differ for different concrete mixtures. Values of these parameters for CC  
13 are defined in *fib*-Bulletin 34 (2006) while for HVFAC values proposed in (Carević et al.,  
14 2019) were used in this study. The only parameter that represents the concrete quality is the  
15 inverse effective carbonation resistance ( $R_{ACC}^{-1}$ ), which is determined based on accelerated  
16 carbonation tests:

$$17 \quad R_{ACC}^{-1} = \left( \frac{x_c}{\sqrt{2 \cdot C_s \cdot t}} \right)^2 \quad (4)$$

18 where


19  $x_c$  accelerated carbonation depth (mm),

20  $C_s$  CO<sub>2</sub> concentration (kg/m<sup>3</sup>),

21  $t$  test duration (s).

22 In order to analyze the impact of concrete type and compressive strength, it is necessary to  
23 establish a relationship between  $R_{ACC}^{-1}$  and 28 days concrete's compressive strength ( $f_{cm}$ ). To

1 establish this relationship, a database of available accelerated carbonation test results for CC  
 2 and HVFAC was formed. This database contained results from 15 studies for CC (Atis, 2003;  
 3 Bouzoubaâ et al., 2010; Bucher et al., 2017; Carević et al., 2019; Dhir et al., 2007; Durán-  
 4 Herrera et al., 2015; Jiang et al., 2000; Katz, 2003; Khunthongkeaw et al., 2006; Kuosa et al.,  
 5 2008; Leemann and Moro, 2017; Ohga and Nagataki, 1989; Pedro et al., 2015; Ribeiro et al.,  
 6 2009; Shah and Bishnoi, 2018) and 8 studies for HVFAC (Atis, 2003; Bentur and Jaegermann,  
 7 1991; Bouzoubaâ et al., 2010; Carević et al., 2019; Ignjatović et al., 2017b; Jia et al., 2012;  
 8 Jiang et al., 2000; Ribeiro et al., 2003). A total of 115 carbonation depth measurements for CC  
 9 and 59 for HVFAC were collected for samples with compressive strength ranging from 11.5 to  
 10 67.0 MPa (measured on a standard cylinder sample Ø150·300 mm). The relationship between  
 11  $R^{-1}_{ACC}$  and  $f_{cm}$  for CC and HVFAC is presented in Figure 2.



1 Figure 2. The relationship between inverse effective carbonation resistance and 28 days  
2 concrete's compressive strength for CC and HVFAC  
3 For both types of concrete power regression function was used, which is in agreement with the  
4 research of other authors (Silva et al., 2015). Coefficient of determination of 0.516 and 0.679  
5 were achieved for CC and HVFAC mixtures, respectively. As expected, HVFAC has a lower  
6 carbonation resistance compared to CC with same compressive strength. However, as  
7 compressive strength increases, the differences between CC and HVFAC are reduced. In further  
8 analysis the relationships proposed for CC and HVFAC and shown in Figure 2 will be used for  
9 the calculation of  $R^{-1}_{ACC}$ .

#### 10 **4.2 Service life prediction**

11 After establishing these relationships, a prediction of the carbonation depth and the service life  
12 based on concrete compressive strength can be made using Eq. (1). Since Eq. (1) represents a  
13 probabilistic approach, the input parameters of the model should be stochastic variables.

14 Distributions and characteristic parameters for some variables ( $f_c$ ,  $g_c$ ,  $RH_{ref}$ ,  $t_c$ ,  $b_c$ ,  $C_s$ ,  $k_t$  and  $\varepsilon_t$ )  
15 are given in *fib*-Bulletin 34 (2006) **for CC and in (Carević and Ignjatović, 2020) for**  
16 **HVFAC**. An overview of the applied distributions and their characteristic parameters is  
17 shown in Table 1.

18 The result of the limit state function is the probability of an event occurring, which in this case  
19 means probability that the carbonation depth will be equal to the concrete cover depth. The  
20 acceptable probability of failure according to *fib*-Bulletin 34 (2006) is 0.10, which corresponds  
21 to a reliability index ( $\beta$ ) of 1.3. The reliability index of limit state function was calculated  
22 using the *First Order Reability Method* (FORM). **The results of this analysis, which serve as**  
23 **input for LCA, are presented in Figures 3 and 4.**


24

1 Table 1. Input parameters of the limit state function for service life prediction

Parameter	Distribution	$\mu$	$\sigma$	Unit	
$RH_{\text{real}}$	Beta	65 (40*)	10 (100*)	%	
$RH_{\text{ref}}$	Constant	65	–	%	
$f_c$	Constant	5.0	–	–	
$g_c$	Constant	2.5	–	–	
$t_c$	Constant	7	–	days	
$b_c$	Normal	-0.567	0.024	–	
$C_s$	Normal	0.0008	0.0001	kg/m <sup>3</sup>	
$t$	Constant	1÷100	–	year	
$k_t$	CC	Normal	1.25	0.35	–
	HVFAC	Normal	3.05	0.85	–
$\varepsilon_t$	CC	Normal	315.5	48	(mm <sup>2</sup> /year)/(kg/m <sup>3</sup> )
	HVFAC	Normal	16264	2440	(mm <sup>2</sup> / year)/(kg/m <sup>3</sup> )
$R^{-1}_{\text{ACC}}$	Normal	Fig. 2	CoV 10%	(mm <sup>2</sup> / year)/(kg/m <sup>3</sup> )	


2 \* Lower and upper limit of the beta distribution

3 The relationship between calculated carbonation depth ( $x_c$ ) and  $f_{\text{cm}}$  for CC and HVFAC  
 4 mixtures is shown in Figure 3. With increasing compressive strength, the carbonation depth  
 5 decreases. For the same compressive strength CC has lower carbonation depth for more than  
 6 two times compared to HVFAC. As a consequence, a higher concrete cover depth for HVFAC  
 7 is required to achieve the same service life as CC. On the other hand, if the same concrete  
 8 cover depth was used for both types of concrete, the service life of HVFAC would be more  
 9 than four times smaller compared to CC (Figure 4).



10

11 Figure 3. The relationship between carbonation depth and compressive strength of CC and  
 12 HVFAC for RH 65% and t=50 years



1

2 Figure 4. Reliability index  $\beta$  during time of exposure for CC and HVFAC

3


#### 4 5. LCA model

5 LCA analysis was performed with a goal of calculating the environmental impacts of RC slab  
 6 and RC beam made of different CC and HVFAC concrete mixes, taking into account two  
 7 approaches to modeling of service life. Impacts were calculated for 43 CC and 51 HVFAC  
 8 mixes, collected from previous research and compiled in databases. Impact category indicators  
 9 were normalized with concrete compressive strength and duration of service life for different  
 10 concrete mixtures and RC member types, and expressed as functions of compressive strength  
 11 applying regression analyses.

#### 12 5.1 System boundaries

13 The analysis was performed for the production stage of the concrete structure life cycle.  
 14 System boundaries were chosen in accordance with the attributional LCI modeling approach  
 15 and shown in Figure 5. Impacts of the plasticizer production were neglected since its mass was  
 16 lower than 0.15 % of the concrete mass. Production of reinforcement was also excluded under  
 17 the assumption that the amount of reinforcement was equal in all compared alternatives, which

1 is required for the same flexural strength of RC members. Impacts from transport to  
 2 construction site and construction itself were assumed to be equal and therefore excluded from  
 3 comparison.



4

5 Figure 5. Analyzed part of the concrete structure life cycle

## 6 5.2 Functional unit

7 An RC slab with effective depth equal to 0.15 m and an RC beam with effective depth equal to  
 8 0.50 m and width equal to 0.30 m were assumed as typical structural members of residential  
 9 and commercial buildings structures. Depth of concrete cover required for service life of 50  
 10 years and indoor environment with relative humidity equal to 65% was calculated for each CC  
 11 and HVFAC mixture (Figure 3). One square meter of RC slab and one linear meter of RC  
 12 beam were taken as FUs.

13 In the approach B (Figure 1) for achieving the same service life of 50 years, volume of  
 14 concrete in FU differed, depending on the type of concrete mixture (CC or HVFAC). Total  
 15 height of CC slab's cross section varied from 0.1723 m to 0.1829 m while total height of  
 16 HVFAC slab' cross section varied from 0.2087 m to 0.2189 m, depending on the mean  
 17 compressive strength. Similarly, total height of CC beam's cross section varied from 0.5333 m  
 18 to 0.5438 m while total height of HVFAC beam's cross section varied from 0.5697 m to  
 19 0.5799 m, depending on the mean compressive strength. Larger concrete cover and

1 consequently, larger total height of cross section was required for HVFAC than for CC  
2 member due to much lower carbonation resistance of HVFAC. However, the volume increase  
3 in the slab case was 20.4% on average while only 7.3% in the beam case.  
4 In the approach A, the concrete cover depth required for service life of 50 years of CC  
5 slab/beam was adopted for HVFAC slab/beam. Consequently, the FU for both CC and  
6 HVFAC slab/beam had the same volume of concrete. However, service life of HVFAC  
7 slab/beam with such concrete cover was much lower than 50 years – calculated values varied  
8 between 4.5 and 8.6 years, Figure 4. Impact category indicators in this approach must be  
9 calculated per year of service life. To enable comparison between approaches A and B,  
10 category indicators calculated according to approach B were also divided by duration of  
11 service life (in this case 50 years for all alternatives).

### 12 **5.3 Life cycle inventory**

13 The intention was to perform LCA in the European context. All Life cycle inventory (LCI)  
14 data were taken as average European data, mostly from the Ecoinvent database (Dones et al.,  
15 2007; Kellenberger et al., 2007; Spielmann et al., 2007) or from European organizations, with  
16 the exception of the FA LCI data. It is very hard to define average data for FA production and  
17 economic allocation – they depend on the particular coal-burning plant technology and cost of  
18 FA and electricity, which differ significantly between European countries. So, Serbian site-  
19 specific data for FA production and allocation were used instead. It was calculated that the  
20 difference in revenue from electricity and FA was over 25%, in which case economic  
21 allocation should be applied (CEN, 2016). Hence, economic allocation, based on the market  
22 prices of FA and electricity, was applied (Marinkovic et al., 2017).

23 Information about LCI sources is summarized in Table 2. **Detailed information on inputs,**  
24 **outputs and resources use for each considered process per unit (kg, m<sup>3</sup> and MJ) and**

1 **quantities of all elementary flows per FU and each concrete mixture are provided in**

2 **Supplementary.**

3 Transport distances were estimated as 100 km (and doubled to account for the return trip) for  
 4 all concrete components and presented in Table 3. For all concrete mixes, it was assumed that  
 5 river NA (sand and round gravel) is transported by barge, while crushed NA (sand and crushed  
 6 gravel) is transported by trucks as is cement and FA.

7 Table 2. Sources of LCI data

Type of data	Source (process name in Ecoinvent V2.0)	Geography
<b>Energy</b>		
Diesel production, distribution, and usage	Ecoinvent (diesel, at regional storage/kg/RER) (diesel, burned in building machine/MJ/GLO)	EU average
Electricity	Ecoinvent (production mix RER/kWh/RER)	EU average
<b>Concrete components</b>		
Cement production	CEMBUREAU (the European Cement Association) EPDs for CEMI and CEMII	EU average
Fine and coarse aggregate production	Ecoinvent (gravel, round, at mine /kg/CH) (gravel, crushed, at mine /kg/CH)	estimated as EU average
FA production	Industry	Serbia
<b>Concrete</b>		
Concrete production	Ecoinvent (concrete, normal, at plant/m <sup>3</sup> /CH)	estimated as EU average
<b>Transport</b>		
Road and river	Ecoinvent (transport, lorry 16–32t, EURO5/tkm/RER) (transport, barge/tkm/RER)	EU average

8

9 Table 3. Transport distances and types

Material	Route		Transport distance (km)	Transport type
	From	To		
Cement	Cement plant	Concrete plant	100 x 2	Truck 16–32 t
River NA	Place of extraction	Concrete plant	100 x 2	Barge 10000 t
Crushed NA	Place of extraction	Concrete plant	100 x 2	Truck 16–32 t
FA	Power plant	Concrete plant	100 x 2	Truck 16–32 t

10

11



## 1 **5.4 Life cycle impact assessment**

2 **The problem-oriented (mid-points) methodology was chosen for the impact assessment.**  
3 **In the damage-oriented approaches (such as for instance Ecoindicator, ReCiPe, etc.), it is**  
4 **not possible to avoid normalization, grouping and weighting. Weighting is not a**  
5 **scientifically based operation, but it relays upon the opinion and attitude of experts**  
6 **towards different environmental effects. On the other hand, the relationship between**  
7 **midpoint category indicators and LCI results is easily established through appropriate,**  
8 **scientifically based, characterization models.**

9 If the use phase is excluded, the most significant emissions in the course of a concrete  
10 structure's life cycle originate from cement production and transport: green-house gasses  
11 (carbon dioxide, methane, and nitrogen dioxide), sulphur dioxide, nitrogen oxide and non-  
12 methane volatile organic compounds (NMVOC). Relevant midpoint impact categories related  
13 to these emissions are climate change, acidification, eutrophication, and photochemical-  
14 oxidant creation (Marinković, 2013). Beside them, energy consumption and especially fossil  
15 fuels consumption are of interest when assessing concrete structures. Therefore, the impact  
16 category indicators calculated in this work were global warming potential (GWP),  
17 eutrophication potential (EP), acidification potential (AP), and photochemical-oxidant creation  
18 potential (POCP). They were calculated using the characterization models within baseline  
19 CML methodology (Guinée et al., 2002) which is most commonly used.

20 Beside these, abiotic depletion of fossil fuels potential (ADPFF) was calculated using the  
21 cumulative energy demand method. For the ADPFF calculations, the following heating values  
22 of fossil fuels were used: 42.0 MJ/kg for diesel, 19.1 MJ/kg and 8.8 MJ/kg for hard and soft  
23 coal respectively, and 39.0 MJ/m<sup>3</sup> for natural gas. For life cycle inventory and life cycle  
24 impact calculations, original Excel-based software was used.

## 1 **5.5 CO<sub>2</sub> uptake**

2 Due to carbonation, certain amount of CO<sub>2</sub> will be reabsorbed or taken up by the concrete  
3 structure over its life cycle. This process has been investigated a lot as an aspect of concrete  
4 durability, but it was rarely taken into account when assessing CO<sub>2</sub> emissions in course of the  
5 life cycle of concrete structures (Garcia-Segura et al., 2014).

6 To assess the CO<sub>2</sub> uptake, it is necessary to consider the use and end-of-life phase of the life  
7 cycle of the concrete structure. The CO<sub>2</sub> uptake generally depends on the earlier uptake during  
8 service life, exposure conditions and time perspective as well as on the size of debris pieces.

9 For instance, if concrete waste is crushed and temporarily stockpiled for a new application the  
10 exposure time is limited. If it is landfilled, the exposure time is much longer – it is not limited  
11 and concrete will eventually fully carbonate. For a very long time perspective, maximum total  
12 potential CO<sub>2</sub> uptake (for all life cycle phases) is estimated as 75% of the maximum clinker  
13 uptake (CEN, 2016). For CEM I concrete, this theoretical maximum CO<sub>2</sub> uptake is about 0.37  
14 kg CO<sub>2</sub>/ kg cement. This amount obviously affects the GWP indicator calculated for the whole  
15 life cycle of the concrete structure.

16 In this work the CO<sub>2</sub> uptake impact was not taken into account since the whole life cycle must  
17 be considered and many assumptions regarding the CO<sub>2</sub> uptake potentials for different  
18 concrete mixtures, service and end-of-life phase scenarios and eventual post-use applications  
19 must be made. While this is acceptable for the purposes of this comparative study, the  
20 influence of CO<sub>2</sub> uptake over the whole life cycle should not be neglected in the sustainability  
21 design of concrete structures.

## 22 **5.5 Uncertainty in LCA**

23 **According to Huijbregts (1998) three types of uncertainty can be distinguished within**  
24 **LCA. First one is parameter uncertainty caused by the imprecise, incomplete, outdated**

1 or missing values of LCI data. The second is model uncertainty, for instance adoption of  
2 linear models instead of non-linear for environmental phenomena modeling. The third is  
3 uncertainty due to choices such as, for instance, choice on system boundaries (which  
4 upstream and downstream flows are included), methodological choices (attributional or  
5 consequential modeling), choice of FU, allocation approaches, etc.

6 Generally, the parameter uncertainty can be dealt with using simplified approach which  
7 includes a qualitative assessment of data quality indicators based on a pedigree matrix  
8 (Weidema & Wesnaes, 1996). Then uncertainty factors are attributed to each of the  
9 quality indicator depending on their scores (1-5) and the square of geometric standard  
10 deviation can be calculated for assumed probability function for each elementary flow.

11 Such procedure is applied in Ecoinvent database where uncertainty factors based on  
12 expert judgments are used (Frischknecht et al., 2007). The uncertainty estimations on the  
13 level of a unit process are then obtained using Monte Carlo simulation. Monte Carlo  
14 analysis is a probabilistic model parameter uncertainty analysis which requires  
15 distribution functions for each elementary flow or unit process. However, it is stated in  
16 this report that “the reliability of the mean values of the unit process raw data is judged  
17 to be much higher as compared to the roughly estimated geometric standard deviation”,  
18 which has to be used for probability function definition and Monte Carlo simulations.

19 Maybe more transparent way to test the uncertainty, especially uncertainty due to  
20 choices, is to perform the sensitivity analysis on the main influencing parameters/choices.  
21 It means that impact assessment is performed for chosen parameter varied within  
22 “realistic” limits and the interval of impact result is obtained instead of one value. This  
23 procedure is commonly used for testing the effect of transportation distances and types  
24 but also it can be used for testing the effect of the service life model (Vieira et al., 2018,  
25 Van den Heede et al., 2017).

1 In this work the parameter uncertainty of LCI data was not tested and sensitivity  
2 analysis regarding transport distances or service life model was not performed. The  
3 rationale behind these choices is as following.

4 Majority of LCI data was taken from Ecoinvent data base. Rather wide geography  
5 (Europe) was chosen because the goal of the study was a methodological issue, not a  
6 comparison between two or more products. Two unit processes that practically  
7 determine the chosen impacts are cement production and transportation. Since the  
8 contribution of aggregate, concrete and fly ash production is low, usually below 5% each  
9 (**referenza dodati Eco efficient construction and building materials**), the uncertainties  
10 regarding the quality of data don't affect the results significantly (not for more than few  
11 percents). Cement production technology is today very similar throughout Europe and  
12 therefore impact category indicators data from the largest European Cement Association  
13 CEMBUREAU EPD's were considered as representative in all aspects for Europe.

14 Transportation is the second largest source of impacts, but still much lower than cement  
15 production in the European context. However, it is not logical to assume that cement,  
16 aggregate and fly ash distances differ for two compared alternatives – both structures  
17 are constructed at the same construction site and supplied from the same concrete plant.

18 Transportation distances and types other than those assumed will influence both  
19 alternatives' impacts in the same way. So, sensitivity analysis regarding transport  
20 distances was not performed since the goal of the study was to establish the effect of  
21 different service life modeling in comparative LCA and not to calculate the absolute  
22 values of impact indicators.

23 What however may introduce relatively large uncertainties (if FU is defined in relation  
24 to service life and compressive strength) is service life prediction model and relationship  
25 between mixture proportions and compressive strength of concrete.

1 **Service life prediction in this work is based on a full probabilistic approach where each**  
2 **parameter is introduced with its estimated distribution function. The calculation of**  
3 **service life is performed for the assumed failure probability equal to 0.1 or reliability**  
4 **index equal to 1.3 which is usually requested regarding service life design of concrete**  
5 **structures. Uncertainties regarding relationship between mixture proportions and**  
6 **compressive strength of concrete are taken into account by applying the statistical**  
7 **regression analysis on a database of 43 CC and 51 HVFAC mixtures.**

8

## 9 **6. Results and discussion**

10 **For each CC and HVFAC mixture from databases, impact assessment of the concrete**  
11 **structure production part of the life cycle was performed two times: once with the same**  
12 **volume of FU (Approach A) and once with corrected volume of FU (Approach B).**

13 Calculated impact category indicators of CC slab/beam and HVAC slab/beam were  
14 normalized relative to their service lives ( $t_{sl}$ ) and mean compressive strength at 28-days ( $f_{cm}$ )  
15 and plotted against it. Regression analysis was performed and functions which best fitted the  
16 experimental results (with the highest determination coefficient  $R^2$ ) were selected. Results for  
17 Approach B are presented in Figures 6–10.


18 A trend of decreasing indicator values with increasing compressive strength is clear for all  
19 indicators and both concrete mixtures. This means that the effect of compressive strength on  
20 indicator values outweighs the effect of the larger cement content needed for the larger  
21 strength.

22 **As already stated, the FU volume increase in the HVFAC slab was 20.4% on average**  
23 **while only 7.3% in the HVFAC beam (compared to CC slab and beam, respectively).**

24 **Despite the larger volume of FU, HVFAC mixtures have lower values of all indicators for**  
25 **both slabs and beams. Significant decrease of cement content ranging between 40% and**


1 60% in analyzed HVFAC mixtures causes such results since cement production is by far  
 2 the largest contributor to all indicators. Fly ash was considered as a by-product and its  
 3 contribution consisted of the environmental load allocated from the electricity  
 4 production and the environmental load from its own treatment prior to the utilization in  
 5 concrete. The economic allocation coefficient calculated for Serbian market prices was  
 6 equal to 0.013 (Marinkovic et al., 2017) and all together contribution of the FA  
 7 production to category indicators was below 5%. Similarly, contribution of concrete and  
 8 aggregate production was around 5% each, while transport contribution depended on  
 9 the category indicator: 10-15% of GWP and 30-35% of ADPFF, EP, AP, and POCP  
 10 originated from transport emissions and resources use.

11




12

13 Figure 6. Normalized GWP of CC slab/beam and HVFAC slab/beam per FU – Approach B



1

2 Figure 7. Normalized ADPPF of CC slab/beam and HVFAC slab/beam per FU – Approach B



3

4 Figure 8. Normalized EP of CC slab/beam and HVFAC slab/beam per FU – Approach B

5 However, the effect of service life is more pronounced for slabs than for beams. For instance,

6 normalized GWP of HVFAC slab is lower for 22% on average, while GWP of HVFAC beam

7 is lower for 30% on average compared to CC slab and CC beam, respectively. Although LCA

8 was performed for same CC and HVFAC mixtures in both cases, the volume increase in the


9 HVFAC slab FU relative to CC slab FU, is larger than in the beam's case. **This is expected**

10 **since concrete cover makes larger part of the unit volume in the slab's case than in the**

11 **beam's case.** So, if Approach B is applied, the effect of service life in LCA depends on the


12 size and type of a structural member.

1



2

3 Figure 9. Normalized AP of CC slab/beam and HVFAC slab/beam per FU – Approach B



4

5 Figure 10. Normalized POCP of CC slab/beam and HVFAC slab/beam per FU – Approach B


6

7 Results for normalized GWP of slab and beam when applying Approach A are shown in

8 Figures 11 and 12. For the sake of comparison, obtained results for Approach B are also


9 shown in these Figures.





1

2 Figure 11. Normalized GWP of CC and HVFAC slab per FU – Approach A and B



3

4 Figure 12. Normalized GWP of CC and HVFAC beam per FU – Approach A and B

5 Similar results were obtained for other impact category indicators. Values of the normalized  
 6 indicators for CC slab/beam are equal regardless of the approach due to the methodology  
 7 applied in this study. However, normalized GWP for HVFAC slab is 6.5 times larger on  
 8 average in Approach A than in Approach B, although it was calculated for same HVFAC mix  
 9 proportions. In the beam's case this ratio is even larger: 7.1 on average. This is the  
 10 consequence of very short service lives obtained for the HVFAC alternatives, if the concrete  
 11 cover depth is assumed equal to required value for CC alternatives and service life of 50 years.

1 It is more than obvious that Approach B is favorable for service life modeling of green  
2 concretes which have poorer durability properties compared to CC. However, it should be kept  
3 in mind that the volume of concrete required for the same structural performance in this  
4 approach is larger for HVFAC alternatives: for 20.4% / 7.3 % on average in the slab/beam  
5 case, respectively.

6 **Results of comparison with other published results are presented in Table 4. Among the**  
7 **published research, papers in which compared alternatives had significantly different**  
8 **service lives were chosen for comparison with own results. In all cases, deterioration**  
9 **mechanism was chloride attack (favorable for green concrete alternative), Approach A**  
10 **was applied and several green alternatives (different replacement ratios of fly ash or**  
11 **slag, but one mix design per alternative) were compared with referent, conventional**  
12 **cement concrete. Only one impact category indicator was chosen for comparison – GWP,**  
13 **except for the work of Vieira et al. (2018) where a single score expressed in points (Pt)**  
14 **obtained with ReCiPe methodology was used. Although Vieira et al. (2018) reported also**  
15 **results for midpoint categories including GWP, it was not clear to authors for which FU**  
16 **these results were obtained. In Van den Heede et al. (2017) GWP was calculated for FU**  
17 **which included volume, and for FU which included volume, strength and service life. To**  
18 **eliminate the impact of compressive strength, from all analyzed alternatives in their**  
19 **work, only concretes with same compressive strength were chosen.**

20

21

22

23

24

25

1 **Table 4. Comparison with published research**

Author	Environ. impact (EI) (mechanism) (1)	Concrete mixture (2)	Durability property (DP) (3)	Service life (SL) (4)	EI(GC)/EI(CC) FU1 <sup>1</sup> average values (5)	EI(GC)/EI(CC) FU2 <sup>2</sup> average values (6)	(5)/(6)
Panesar et al. (2017)	GWP (chloride ingress)	cement concrete (CC) <sup>3</sup>	28-day rapid chloride permeability (3186 C)	/	0.65	0.09	7.2
		25% of cement replaced with slag and 8% of silica fume (GC) <sup>4</sup>	28-day rapid chloride permeability (421 C)	/			
Vieira et al. (2018)	Pt <sup>5</sup> (chloride ingress)	cement concrete (CC)	/	8.4 years	1.07	0.30	3.6
		40% of cement replaced with fly ash (GC)	/	29.1 years			
Van den Heede et al. (2017)	GWP (chloride ingress)	cement concrete (CC)	/	32 years	0.98 (approx.)	0.29 (approx.)	3.4
		15% of cement replaced with fly ash (GC)	/	100 years for FU calculation			
this work	GWP (carbonation)	cement concrete (CC)	/	50 years	/	3.6-9.7 (slab, Approach A)	/
		40%-60% of cement replaced with fly ash (GC)	/	4.5-8.6 years			

2 <sup>1</sup>FU1 (includes volume and strength)

3 <sup>2</sup>FU2 (includes volume, strength, and SL or DP)

4 <sup>3</sup> conventional cement concrete alternative

5 <sup>4</sup> green concrete alternative

6 <sup>5</sup> single score including damage to human health, ecosystems, and resources

7

8

1 It can be seen from Table 4 that including the service life into FU significantly changed  
2 the impact assessment result expressed as ratio between GC and CC impact, for 3.4 to  
3 7.5 times. In this work the FU including volume and strength was not tested so only the  
4 result in column (6) is reported. However, results are similar having in mind that in this  
5 work green concrete alternative has poorer durability related behavior – if expressed as  
6 ratio  $EI(CC)/EI(GC)$ , result in column (6) for this work would be 0.10 – 0.28 which is  
7 very similar to results of other researchers.

8 Results shown in Figures 6-12 clearly demonstrate large scatter ( $R^2$  ranges between  
9 0.1604 and 0.5983, where the correlation coefficient  $R$  represents the degree of  
10 correlation between two variables) especially for the GWP which is most influenced by  
11 the cement amount. For the same compressive strength calculated impacts vary a lot  
12 both for CC and HVFAC for the reasons explained in Chapter 3. Standard deviation and  
13 coefficient of variance (CoV) of GWP prediction (Approach B, slab) are calculated for  
14 several strength intervals (38-45 MPa, 45-50 MPa and 50-55 MPa) for both CC and  
15 HVFAC and presented in Table 5.

16 **Table 5. GWP/( $f_{cm} \cdot t_{sl}$ ), Approach B, slab**

Compressive strength $f_{cm}$		CC	HVFAC
38-45 MPa	average (gCO <sub>2</sub> -eq./MPa·year)	34.7	28.0
	standard deviation (gCO <sub>2</sub> -eq./MPa·year)	4.72	4.53
	coefficient of variance (%)	13.6	16.2
45-50 MPa	average (gCO <sub>2</sub> -eq./MPa·year)	32.5	27.1
	standard deviation (gCO <sub>2</sub> -eq./MPa·year)	3.99	4.32
	coefficient of variance (%)	12.3	15.9
50-55 MPa	average (gCO <sub>2</sub> -eq./MPa·year)	30.7	23.7
	standard deviation (gCO <sub>2</sub> -eq./MPa·year)	4.18	4.05
	coefficient of variance (%)	13.6	17.1

17

18 The uncertainty expressed through standard deviation or coefficient of variance is rather  
19 large, larger for HVFAC (CoV ranges between 15.9% and 17.1%) than for CC concrete  
20 (CoV ranges between 12.3% and 13.6%). This analysis shows that compressive strength

1 **dependence on the mix design introduces similar, maybe even larger uncertainty than**  
2 **that brought by the LCI environmental data uncertainty if Monte Carlo simulation is**  
3 **performed (see for instance Van den Heede et al. (2017)). All together, this level of**  
4 **uncertainty cannot jeopardize the conclusions' validity since Approaches A and B lead to**  
5 **impacts which values differ for an order of magnitude.**

6

## 7 **7. Conclusions**

8 In comparative LCA of reinforced concrete structures, it is necessary that compared  
9 alternatives fulfill all relevant functional requirements of the concrete structure (safety,  
10 serviceability and durability). Since conventional and green concretes have different  
11 mechanical and durability related properties, this goal can be achieved either by correcting the  
12 volume of FU (Approach B) or by normalizing the calculated impact indicators with  
13 compressive strength and duration of service life (Approach A).

14 In this work both approaches were tested to show how different modeling of service life in  
15 LCA affects the environmental impacts of different RC structural members. Two concrete  
16 mixes, CC and HVFAC, and one deterioration mechanism - carbonation, were chosen for this  
17 demonstration. For two types of structural members, slab and beam, relationships between the  
18 chosen normalized impact category indicators and compressive strength were derived. They  
19 were developed using a number of experimental results reported in literature regarding the  
20 mixture proportions and properties of the mentioned concrete mixes. Regression analyses were  
21 applied to the obtained LCA results concerning normalized GWP, ADPFF, EP, AP, and POCP  
22 indicators and best-fitting equations relating normalized indicators and concrete compressive  
23 strength were selected. Finally, comparison of the results obtained according to these two  
24 approaches was performed.

1 For service life modeling in the case of carbonation a *fib*-Bulletin 34 (2006) model was  
2 applied with missing required parameters for HVFAC mixtures adopted according to (Carević  
3 et al., 2019). The relationships between inverse effective carbonation resistance and  
4 compressive strength for both concrete mixtures were derived on the basis of test results from  
5 literature applying regression analysis. Following conclusions are drawn.

6 1. Results obtained using developed service life prediction model showed that HVFAC  
7 mixtures had much lower carbonation resistance compared to CC mixtures. Consequently, for  
8 the same depth of concrete cover, RC member made of HVFAC had much shorter service life  
9 (6 to 11 times, depending on the compressive strength) than RC member made of CC.

10 2. LCA was performed on a relatively large number of mixes (43 CC and 51 HVFAC) with a  
11 very broad range of involved parameters which caused a high scatter of results. **The**  
12 **uncertainty regarding the relationship between mixture proportions and compressive**  
13 **strength of concrete was assessed. The parameter uncertainty was not assessed which is a**  
14 **limitation of the work. It was considered that this fact did not have a significant effect on**  
15 **the conclusions in this study having in mind its goal and range of obtained results.**

16 3. If Approach A is applied (same volume of FU) all normalized impact indicators of HVFAC  
17 mixtures, for both slabs and beams, were much larger than those of CC mixtures. Depending  
18 on the impact indicator and compressive strength this increase ranges between 5 and 8, which  
19 is almost an order of magnitude. This is a consequence of a much lower carbonation resistance  
20 (shorter service life) of HVFAC compared to that of CC.

21 4. If Approach B is applied (different volume of FU) all normalized impact indicators of  
22 HVFAC mixtures, for both slabs and beams, were lower than those of CC mixtures. This  
23 decrease ranges between 4% and 30% depending on the impact indicator and compressive  
24 strength. In this specific case, the volume increase in the slab FU was 20.4% on average while

1 only 7.3% in the beam FU; because of that, the effect of service life was more pronounced for  
2 slabs than for beams.

3 5. Different modeling of service life in LCA of concrete structures can result in totally  
4 different - opposite conclusions. With slightly larger volume, which of course increases the  
5 weight and cost of the structure, calculated normalized impact indicators of HVFAC structural  
6 members were lower for an order of magnitude. Rejection of green concretes with poorer  
7 durability properties based only on the service life modeling like in Approach A is not  
8 justified, because it is possible to achieve equal structural performance to CC performance  
9 with slightly larger volume of RC member. **In a word, a caution is recommended when**  
10 **drawing conclusions based only on an Approach A like type of service life modeling in**  
11 **LCA of concrete structures.**

12 **6. Commonly used Approach A is not applicable for the environmental assessment of**  
13 **concrete structures in practice. This is because compared alternatives must fulfill same**  
14 **functional requirements – these are strength, serviceability (deformations mostly) and**  
15 **service life duration in the case of concrete structures. Normally, concrete structure is**  
16 **designed to fulfill them and results of design are different if different concrete mixtures**  
17 **are used (different size dimensions, different reinforcement amount, different concrete**  
18 **cover depth etc.). So, in practice, FU in comparative environmental assessments should**  
19 **be the structure as a whole – in fact there is no other way. For the final choice of “best”**  
20 **alternative, other aspects should also be included (various specific technical aspects**  
21 **regarding for instance the construction, cost etc.) which implies multicriteria**  
22 **optimization as adequate methodology for integrated assessment.**

23 **7. Future research in the area of the environmental assessment of concrete structures**  
24 **should be oriented towards developing CO<sub>2</sub> uptake prediction model for different green**  
25 **concretes such as RAC or HVFAC, and for different end-of-life scenarios. This should**

1 enable proper assessment of CO<sub>2</sub> balance over the whole life cycle of a concrete  
2 structure. Also, research should be devoted to life cycle integrated assessment of concrete  
3 structures taking into account various possible choices on the importance associated to  
4 different functional aspects of the concrete structure.

5 **8. Results and conclusions in this work are valid for analyzed concrete mixtures,**  
6 **deterioration mechanism and exposure conditions as well as for types of structural**  
7 **members chosen in demonstration example. They should not be generalized – results of**  
8 **the environmental assessment of a concrete structure depend on the purpose of the**  
9 **construction project, type of the structure and structural members, exposure conditions,**  
10 **and many other factors - it is a case-dependent issue.**

11

## 12 **Acknowledgements**

13 This work was supported by the Ministry for Education, Science and Technology, Republic of  
14 Serbia and through the research project TR36017: 'Utilization of by-products and recycled  
15 waste materials in concrete composites in the scope of sustainable construction development  
16 in Serbia: investigation and environmental assessment of possible applications'. This support  
17 is gratefully acknowledged.

## 18 **References**

19 Ajdukiewicz, A.B., Kliszczewicz, A.T., 2007. Comparative tests of beams and columns made  
20 of recycled aggregate concrete and natural aggregate concrete. J. Adv. Concr. Technol. 5,  
21 259–273. <https://doi.org/doi:10.3151/jact.5.259>.

22 Arezoumandi, M., Volz, J.S., 2013. Effect of fly ash replacement level on the shear strength of  
23 high-volume fly ash concrete beams. J. Clean. Prod. 59, 120–130.

24 <https://doi.org/10.1016/j.jclepro.2013.06.043>



1 Arezoumandi, M., Smith, A., Volz, J.S., Khayat, K.H., 2014. An experimental study on shear  
2 strength of reinforced concrete beams with 100% recycled concrete aggregate. *Constr.*  
3 *Build. Mater.* 53, 612–620. <https://doi.org/doi:10.1016/j.conbuildmat.2013.12.019>.

4 ASTM C618, 2015. Standard Specification for Coal Fly Ash and Raw or Calcined Natural  
5 Pozzolan for Use in Concrete. West Conshohocken, Pennsylvania.

6 Atis, C.D., 2003. Accelerated carbonation and testing of concrete made with fly ash. *Constr.*  
7 *Build. Mater.* 17, 147–152. [https://doi.org/10.1016/S0950-0618\(02\)00116-2](https://doi.org/10.1016/S0950-0618(02)00116-2)

8 Balakrishnan, B., Awal, A.S.M.A., 2014. Durability Properties of Concrete Containing High  
9 Volume Malaysian Fly Ash. *Int. J. Res. Eng. Technol.* 03, 529–533.

10 Bentur, A., Jaegermann, C., 1991. Effect of curing and composition on the properties of the  
11 Outer skin concrete. *J. Mater. Civ. Eng.* 3, 252–262.

12 Berndt, M. L., 2009. Properties of sustainable concrete containing fly ash, slag and recycled  
13 concrete aggregate. *Construction and Building Materials* 23, 2606–2613. doi:  
14 [10.1016/j.conbuildmat.2009.02.011](https://doi.org/10.1016/j.conbuildmat.2009.02.011).

15 Bhaskara, G. S. V., Rao, K. B. and Anoop, M. B., 2018. Model for compressive strength  
16 development of OPC concrete and fly ash concrete with time. *Magazine of Concrete*  
17 *Research*, 70(11), 541–557. doi: [10.1680/jmacr.17.00203](https://doi.org/10.1680/jmacr.17.00203).

18 Bortz, B. S., 2008. Salt-scaling Durability of Fly Ash Concrete, Thesis. Kansas State  
19 University.

20 Bouzoubaâ, N., Fournier, B., 2003. Optimization of fly ash content in concrete Part I: Non-air-  
21 entrained concrete made without superplasticizer. *Cem. Concr. Res.* 33, 1029–1037.  
22 [https://doi.org/10.1016/S0008-8846\(03\)00004-8](https://doi.org/10.1016/S0008-8846(03)00004-8)

23 Bouzoubaâ, N., Bilodeau, A., Tamtsia, B., Foo, S., 2010. Carbonation of fly ash concrete:  
24 laboratory and field data. *Can. J. Civ. Eng.* 37, 1535–1549. [https://doi.org/10.1139/L10-](https://doi.org/10.1139/L10-081)  
25 [081](https://doi.org/10.1139/L10-081)

1 **Braga, A.M., Silvestre, J.D., de Brito, J., 2017. Compared environmental and economic**  
2 **impact from cradle to gate of concrete with natural and recycled coarse aggregates.**  
3 **J. Clean. Prod. 162, 529–543.**  
4 **<http://dx.doi.org/10.1016/j.jclepro.2017.06.057>**

5 Bucher, R., Diederich, P., Escadeillas, G., Cyr, M., 2017. Service life of metakaolin-based  
6 concrete exposed to carbonation: Comparison with blended cement containing fly ash,  
7 blast furnace slag and limestone filler. Cem. Concr. Res. 99, 18–29.  
8 <https://doi.org/10.1016/j.cemconres.2017.04.013>

9 Burden, D., 2006. The Durability of Concrete Containing High Levels of Fly Ash. The  
10 university of New Brunswick.

11 Carette, G., Bilodeau, A., Chevrier, R.L., Malhotra, V.M., 1993. Mechanical Properties of  
12 Concrete Incorporating High Volumes of Fly Ash From Sources in the U.S. Mater. J. 90,  
13 535–544.

14 Carević, V., Ignjatović, I., Dragaš, J., 2019. Model for practical carbonation depth prediction  
15 for high volume fly ash concrete and recycled aggregate concrete. Constr. Build. Mater.  
16 213, 194–208. <https://doi.org/10.1016/j.conbuildmat.2019.03.267>

17 **Carević, V., Ignjatović, I., 2020. Evaluation of concrete cover depth for green concretes**  
18 **exposed to carbonation. Struct. Concr. <https://doi.org/10.1002/suco.202000086>**

19 **Celik, K., Meral, C., Petek Gursel, A., Mehta, P.K., Horvath, A., Monteiro, P.J.M., 2015.**  
20 **Mechanical properties, durability, and life-cycle assessment of self-consolidating**  
21 **concrete mixtures made with blended portland cements containing fly ash and limestone**  
22 **powder. Cem. Concr. Compos. 56, 59–72. doi:10.1016/j.cemconcomp.2014.11.003**

23 CEN, 2016. EN 16757-Sustainability of construction works - Environmental product  
24 declarations - Product Category Rules for concrete and concrete elements. European  
25 Committee for Standardization, Brussels, Belgium.

- 1 CEN, 2011. EN 206-1: Concrete – Part 1: Specification performance, production and  
2 conformity. European Committee for Standardization, Brussels, Belgium.
- 3 CEN, 2008. EN 196-1: Methods of testing cement - Part 1: Determination of strength.  
4 European Committee for Standardization, Brussels.
- 5 CEN, 2004. EN 1992-1-1: Design of concrete structures - Part 1-1: General rules and rules for  
6 buildings. European Committee for Standardization, Brussels, Belgium.
- 7 **CEN, 2002. EN 1990: Basis of structural design. European Committee for**  
8 **Standardization, Brussels, Belgium.**
- 9 **De Schepper, M., Van den Heede, P., Van Driessche, I., De Belie, N., 2014. Life Cycle**  
10 **Assessment of Completely Recyclable Concrete. Materials (Basel). 7, 6010–6027.**  
11 <https://doi.org/10.3390/ma7086010>
- 12 Dhir, R.K., Limbachiya, M.C., McCarthy, M.J., Chaipanich, A., 2007. Evaluation of Portland  
13 limestone cements for use in concrete construction. Mater. Struct. Constr. 40, 459–473.  
14 <https://doi.org/10.1617/s11527-006-9143-7>
- 15 Dinakar, P., Babu, K. G. and Santhanam, M., 2008. Durability properties of high volume fly  
16 ash self compacting concretes. Cement and Concrete Composites, 30, 880–886. doi:  
17 10.1016/j.cemconcomp.2008.06.011.
- 18 Dones, R., Bauer, C., Bolliger, R., Burger, B., Heck, T., Röder, A., Paul Scherrer Institut,  
19 Emmenegger, M.F., Frischknecht, R., Jungbluth, N., Tuchsmid, M., 2007. Life cycle  
20 inventories of energy systems: results for current systems in Switzerland and other UCTE  
21 countries. ecoinvent report No.5.
- 22 Dragaš, J., Tošić, N., Ignjatović, I., Marinković, S., 2016. Mechanical and time-dependent  
23 properties of high-volume fly ash concrete for structural use. Mag. Concr. Res. 68, 632–  
24 645. <https://doi.org/10.1680/jmacr.15.0038>
- 25 Durán-Herrera, A., Mendoza-Rangel, J.M., De-Los-Santos, E.U., Vázquez, F., Valdez, P.,

1       Bentz, D.P., 2015. Accelerated and natural carbonation of concretes with internal curing  
2       and shrinkage/viscosity modifiers. *Mater. Struct. Constr.* 48, 1207–1214.  
3       <https://doi.org/10.1617/s11527-013-0226-y>

4       Fennis, S.A.A.M., Walraven, J.C., 2012. Using particle packing technology for sustainable  
5       concrete mixture design. *Heron* 57, 73–101.

6       fib-Bulletin 34, 2006. Model Code for Service Life Design, 1st ed. International Federation for  
7       Structural Concrete (fib), Lausanne, Switzerland.

8       **Frischknecht, R., Jungbluth, M., Althaus, H.J., Doka, G., Heck, T., Hellwg, S., Hischier,**  
9       **R., Nemecek, T., Rebitzer, G., Spielmann, M., Wernrt, G., 2007. Overview and**  
10       **Methodology. Ecoivent report No.1. Swiss Centre for Life Cycle Inventories,**  
11       **Dübendorf.**

12       Garcez, M.R., Rohden, A.B., Graupner de Godoy, L.G., 2018. The role of concrete  
13       compressive strength on the service life and life cycle of a RC structure: Case study. *J.*  
14       *Clean. Prod.* 172, 27–38. <https://doi.org/10.1016/j.jclepro.2017.10.153>

15       García-Segura, T., Yepes, V., Alcalá, J., 2014. Life cycle greenhouse gas emissions of blended  
16       cement concrete including carbonation and durability. *Int J Life Cycle Assess* 19, 3–12.

17       Guinée, J.B., Gorrae, M., Heijungs, R., Huppes, G., Kleijn, R., de Koning, A., van Oers, L.,  
18       Wegener Sleeswijk, A., Suh, S., Udo de Haes, H.A., de Bruijn, H., van Duin, R.,  
19       Huijbregts, M.A.J., 2002. Handbook on life cycle assessment. Operational guide to the  
20       ISO standards. I: LCA in perspective. Iia: Guide. Iib: Operational annex. III: Scientific  
21       background. Kluwer Academic Publishers, Dordrecht.  
22       <https://doi.org/10.1007/BF02978784>

23       Huang, C. H. et al., 2013. Mix proportions and mechanical properties of concrete containing  
24       very high-volume of Class F fly ash. *Construction and Building Materials* 46, 71–78. doi:  
25       10.1016/j.conbuildmat.2013.04.016.

- 1 **Huijbregts, M.A., 1998. Application of uncertainty and variability in LCA. International**  
2 **Journal of Life Cycle Assessment 3(5): 273–280.**  
3 <https://doi.org/10.1007/BF02979835>.
- 4 Hung, H.H., 1997. Properties of High Volume Fly Ash Concrete. Faculty of Engineering,  
5 University of Sheffield.
- 6 Ignjatović, I., Marinković, S., Mišković, Z., Savić, A., 2013. Flexural behavior of reinforced  
7 recycled aggregate concrete beams under short-term loading. Mater. Struct. 46, 1045–  
8 1059. <https://doi.org/10.1617/s11527-012-9952-9>
- 9 Ignjatović, I., Marinković, S., Tošić, N., 2017a. Shear behaviour of recycled aggregate  
10 concrete beams with and without shear reinforcement. Eng. Struct. 141, 386–401.  
11 <https://doi.org/10.1016/j.engstruct.2017.03.026>
- 12 Ignjatović, I., Carevic, V., Sas, Z., Dragas, J., 2017b. High volume fly ash concrete: Part 2:  
13 Durability and radiological properties, in: Proceedings of the 17th International  
14 Symposium of MASE. MASE, Ohrid, Macedonia, pp. 700–709.
- 15 IEA, CSI, Technology Roadmap: Low-Carbon Transition in the Cement Industry,  
16 OECD/IEA.; WBCSD, France, march 2018.  
17 [https://www.iea.org/publications/freepublications/publication/TechnologyRoadmapLowC](https://www.iea.org/publications/freepublications/publication/TechnologyRoadmapLowCarbonTransitionintheCementIndustry.pdf)  
18 [arbonTransitionintheCementIndustry.pdf](https://www.iea.org/publications/freepublications/publication/TechnologyRoadmapLowCarbonTransitionintheCementIndustry.pdf)
- 19 ISO, 2006. ISO 14041:2006 - Environmental management — Life cycle assessment — Goal  
20 and scope definition — Inventory analysis. <https://doi.org/10.1007/BF02979337>
- 21 Jia, Y., Aruhan, B., Yan, P., 2012. Natural and accelerated carbonation of concrete containing  
22 fly ash and GGBS after different initial curing period. Mag. Concr. Res. 64, 143–150.  
23 <https://doi.org/10.1680/mac.10.00134>
- 24 Jiang, L., Lin, B., Cai, Y., 2000. A model for predicting carbonation of high-volume fly ash  
25 concrete. Cem. Concr. Res. 30, 699–702. [https://doi.org/10.1016/S0008-8846\(00\)00227-](https://doi.org/10.1016/S0008-8846(00)00227-)

1 1

2 Jiang, L. H. and Malhotra, V. M., 2000. Reduction in water demand of non-air-entrained  
3 concrete incorporating large volumes of fly ash. *Cement and Concrete Research*, 30(11),  
4 1785–1789. doi: 10.1016/S0008-8846(00)00397-5.

5 **Jiménez, C., Barra, M., Josa, A., Valls, S., 2015. LCA of recycled and conventional**  
6 **concretes designed using the Equivalent Mortar Volume and classic methods.**  
7 **Constr. Build. Mater. 84, 245–252. doi:10.1016/j.conbuildmat.2015.03.051**

8 John, V.M., Damineli, B.L., Quattrone, M., Pileggi, R.G., 2018. Fillers in cementitious  
9 materials — Experience, recent advances and future potential. *Cem. Concr. Res.* 114, 65–  
10 78. <https://doi.org/10.1016/j.cemconres.2017.09.013>

11 Katz, A., 2003. Properties of concrete made with recycled aggregate from partially hydrated  
12 old concrete. *Cem. Concr. Res.* 33, 703–711. [https://doi.org/10.1016/S0008-](https://doi.org/10.1016/S0008-8846(02)01033-5)  
13 [8846\(02\)01033-5](https://doi.org/10.1016/S0008-8846(02)01033-5)

14 Kellenberger, D., Althaus, H., Jungbluth, N., Künniger, R., Lehmann, M., Thalmann, P., 2007.  
15 Life Cycle Inventories of Building Products. Final report ecoinvent data v2.0 No.7.

16 Khunthongkeaw, J., Tangtermsirikul, S., Leelawat, T., 2006. A study on carbonation depth  
17 prediction for fly ash concrete.pdf. *Constr. Build. Mater.* 20, 744–753.

18 Knaack, A.M., Kurama, Y.C., 2015. Sustained Service Load Behavior of Concrete Beams  
19 with Recycled Concrete Aggregates. *ACI Struct. J.* 112, 565–578.  
20 <https://doi.org/doi:10.14359/51687799>.

21 **Knoeri, C., Sanyé-Mengual, E., Althaus, H.-J., 2013. Comparative LCA of recycled and**  
22 **conventional concrete for structural applications. Int. J. Life Cycle Assess. 18, 909–**  
23 **918.**

24 Kou, S.C., Poon, C.S., Chan, D., 2007. Influence of Fly Ash as Cement Replacement on the  
25 Properties of Recycled Aggregate Concrete. *J. Mater. Civ. Eng.* 709–717.

1 Kuosa, H., Vesikari, E., Holt, E., Leivo, M., 2008. Field and Laboratory Testing and Service  
2 Life Modelling in Finland, in: Nordic Exposure Sites: Input to Revisions of EN206-1.  
3 Workshop Proceeding from a Nordic Miniseminar. The Nordic Concrete Federation,  
4 Hirtshals, Denmark, pp. 181–208.

5 Lam, L., Wong, Y. L. and Poon, C. S. (1998) ‘Effect of fly ash and silica fume on  
6 compressive and fracture behaviors of concrete’, *Cement and Concrete Research*, 28(2),  
7 pp. 271–283.

8 Langley, W.S., Carette, G.G., Malhotra, V.M., 1989. Structural Concrete Incorporating High  
9 Volumes of ASTM Class Fly Ash. *Mater. Lett.* 86, 507–514.

10 Leemann, A., Moro, F., 2017. Carbonation of concrete: the role of CO<sub>2</sub> concentration, relative  
11 humidity and CO<sub>2</sub> buffer capacity. *Mater. Struct.* 50, 1–14.  
12 <https://doi.org/10.1617/s11527-016-0917-2>

13 Marinković, S., 2013. Life cycle assessment (LCA) aspects of concrete, in: Eco-Efficient  
14 Concrete. pp. 45–80. <https://doi.org/10.1533/9780857098993.1.45>

15 Marinković, S., Dragaš, J., Ignjatović, I., Tošić, N., 2017. Environmental assessment of green  
16 concretes for structural use. *J. Clean. Prod.* 154, 633–649.  
17 <https://doi.org/10.1016/j.jclepro.2017.04.015>

18 Mathur, V.K., Verma, C.L., Gupta, B.S., Agarwal, S.K., Kumar, A., 2005. Use of high volume  
19 fly ash in concrete for building sector. Ottawa, Ontario.

20 McCarthy, M. J. and Dhir, R. K., 2005. Development of high volume fly ash cements for use  
21 in concrete construction. *Fuel*, 84(11), pp. 1423–1432. doi: 10.1016/j.fuel.2004.08.029.

22 Mittal, A., Kaisare, M. B. and Rajenderakumar, S., 2005. Experimental study on use of fly ash  
23 in concrete. Available at:  
24 [https://www.sefindia.org/forum/files/experimental\\_study\\_on\\_use\\_of\\_fly\\_ash\\_in\\_concret](https://www.sefindia.org/forum/files/experimental_study_on_use_of_fly_ash_in_concrete_by_mr_amit_mittal_136.pdf)  
25 [e\\_by\\_mr\\_amit\\_mittal\\_136.pdf](https://www.sefindia.org/forum/files/experimental_study_on_use_of_fly_ash_in_concrete_by_mr_amit_mittal_136.pdf) (Accessed: 22 January 2018).

- 1 Mukherjee, S., Mandal, S., Adhikari, U.B., Ash, F., 2013. Comparative Study on Physical and  
2 Mechanical Properties of High Slump and Zero Slump High Volume Fly Ash Concrete  
3 (HVFAC). *Glob. NEST J.* 15, 578–584.
- 4 Naik, T., Sivasundaram, V., Singh, S.S., 1991. Use of high-volume class f fly ash for  
5 structural grade concrete. *Transp. Res. Rec.* 40–47.
- 6 Nath, P., 2010. Durability of Concrete Using Fly Ash as a Partial Replacement of Cement.  
7 Curtin University of Technology.
- 8 Ohga, H., Nagataki, S., 1989. Prediction and evaluation of the depth of carbonation of  
9 concrete by the accelerated test. *Concr. Libr. JSCE* 93–106.
- 10 Pacheco J., Brito, J. De, Soares, D., 2015. Destructive Horizontal Load Tests of Full-scale  
11 Recycled Aggregate. *ACI Struct. J.* 112, 815–826.
- 12 Panesar, D.K., Seto, K.E., Churchill, C.J., 2017. Impact of the selection of functional unit on  
13 the life cycle assessment of green concrete. *Int. J. Life Cycle Assess.* 22, 1969–1986.  
14 <https://doi.org/10.1007/s11367-017-1284-0>
- 15 Pedro, D., de Brito, J., Evangelista, L., 2015. Performance of concrete made with aggregates  
16 recycled from precasting industry waste: influence of the crushing process. *Mater. Struct.*  
17 *Constr.* 48, 3965–3978. <https://doi.org/10.1617/s11527-014-0456-7>
- 18 Purnell, P., 2012. Material Nature versus Structural Nature: The embodied Carbon of  
19 Fundamental Structural Elements. *Environmental Science&Technology* 46, 454–461
- 20 Quan, H. and Kasami, H., 2013. Experimental Study on Effects of Type and Replacement  
21 Ratio of Fly Ash on Strength and Durability of Concrete. *The Open Civil Engineering*  
22 *Journal*, (7), 93–100.
- 23 Ribeiro, A.B., Machado, A., Gonçalves, A., Salta, M., 2003. A contribution to the  
24 development of performance-related design methods, in: 2nd International RILEM  
25 Workshop on Life Prediction and Aging Management of Concrete Structures. pp. 223–



1           235. <https://doi.org/10.1617/2912143780.022>

2   Ribeiro, M.S.S., Ribeiro, A.B., Gonçalves, A.F., 2009. Resistance of Concrete to Carbonation.

3           Predicted and measured values in natural exposure, in: 2nd International RILEM

4           Workshop on Concrete Durability and Service Life Planning. pp. 229–236.

5   Sadati, S., Arezoumandi, M., Khayat, K.H., Volz, J.S., 2016. Shear performance of reinforced

6           concrete beams incorporating recycled concrete aggregate and high-volume fly ash. *J.*

7           *Clean. Prod.* 115, 284–293. <https://doi.org/10.1016/j.jclepro.2015.12.017>

8   Seara-Paz, S., González-Fonteboa, B., Martínez-Abella, F., Carro-López, D., 2018. Long-term

9           flexural performance of reinforced concrete beams with recycled coarse aggregates.

10          *Constr. Build. Mater.* 176, 593–607. <https://doi.org/10.1016/j.conbuildmat.2018.05.069>

11   Shah, V., Bishnoi, S., 2018. Carbonation resistance of cements containing supplementary

12          cementitious materials and its relation to various parameters of concrete. *Constr. Build.*

13          *Mater.* 178, 219–232. <https://doi.org/10.1016/j.conbuildmat.2018.05.162>

14   Silva, R. V., Neves, R., De Brito, J., Dhir, R.K., 2015. Carbonation behaviour of recycled

15          aggregate concrete. *Cem. Concr. Compos.* 62, 22–32.

16          <https://doi.org/10.1016/j.cemconcomp.2015.04.017>

17   Silva, M.G., Saade M.R.M., Gomes, V., 2013. Influence of service life, strength and cement

18          type on life cycle environmental performance of concrete. *Ibracon Structures and*

19          *Materials journal* 6(6), 844-853.

20   Sivasundaram, V., Carette, G.G., Malhotra, V.M., 1991. Mechanical Properties, Creep, and

21          Resistance to Diffusion of Chloride Ions of Concretes Incorporating High Volumes of

22          ASTM Class F Fly Ashes from Seven Different Sources. *ACI Mater. J.* 88, 407–416.

23   Soman, M. and K. Sobha, 2014. Strength and Behaviour of High Volume Fly Ash Concrete.

24          *International Journal of Innovative Research in Science, Engineering and Technology,*

25          3(5), 12416–12424.

- 1 Spielmann, M., Bauer, C., Dones, R., Tuchschnid, M., 2007. Transport Services.ecoinvent  
2 report NO.14.
- 3 Sunayana, S., Barai, S. V, 2017. Recycled aggregate concrete incorporating fly ash :  
4 Comparative study on particle packing and conventional method. Constr. Build. Mater.  
5 156, 376–386. <https://doi.org/10.1016/j.conbuildmat.2017.08.132>
- 6 **Teixeira, E.R., Mateus, R., Camõesa, A.F., Bragança, L., Branco, F.G., 2016.**  
7 **Comparative environmental life-cycle analysis of concretes using biomass and coal**  
8 **fly ashes as partial cement replacement material. J. Clean. Prod. 112, 2221–2230.**  
9 **doi:10.1016/j.jclepro.2015.09.124**
- 10 Tošić, N., Marinković, S., Ignjatović, I., 2016. A database on flexural and shear strength of  
11 reinforced recycled aggregate concrete beams and comparison to Eurocode 2 predictions.  
12 Constr. Build. Mater. 127, 932–944. <https://doi.org/10.1016/j.conbuildmat.2016.10.058>
- 13 Tošić, N., Marinković, S., Pecić, N., Ignjatović, I., Dragaš, J., 2018. Long-term behaviour of  
14 reinforced beams made with natural or recycled aggregate concrete and high-volume fly  
15 ash concrete. Constr. Build. Mater. 176.  
16 <https://doi.org/10.1016/j.conbuildmat.2018.05.002>
- 17 **Turk, J., Cotic, Z., Mladenovic, A., Sajna, A., 2015. Environmental evaluation of green**  
18 **concretes versus conventional concrete by means of LCA. Waste Manag. 45, 194–**  
19 **205. doi:10.1016/j.wasman.2015.06.035**
- 20 UN Environment, Scrivener, K.L., Vanderley M. John, V.M., Gartner, E.M., 2018. Eco-  
21 efficient cements: Potential economically viable solutions for a low-CO<sub>2</sub> cement based  
22 materials industry, Cem. Concr. Res. 114, 2–26.  
23 <https://doi.org/10.1016/j.cemconres.2018.03.015>
- 24 Van den Heede, P., De Belie, N., 2014. A service life based global warming potential for high-  
25 volume fly ash concrete exposed to carbonation. Constr. Build. Mater. 55, 183–193.

- 1 <http://dx.doi.org/10.1016/j.conbuildmat.2014.01.033>
- 2 **Van den Heede, P., De Keersmaecker, M., Elia, A., Adriaens A., De Belie, N., 2017.**
- 3 **Service life and global warming potential of chloride exposed concrete with high**
- 4 **volumes of fly ash. *Cem. Concr. Compos.* 80, 210–223.**
- 5 <http://dx.doi.org/10.1016/j.cemconcomp.2017.03.020>
- 6 Vieira, D. R., Calmon, J. L., Zulcão, R., Coelho, F.Z., 2018. Consideration of strength and
- 7 service life in cradle-to-gate life cycle assessment of self-compacting concrete in a
- 8 maritime area: a study in the Brazilian context. *Environ.Dev.Sustain.* 20, 1849–1871.
- 9 WBCSD, 2009. The Cement Sustainability Initiative [<http://www.wbcscement.org/pdf/CSI->
- 10 [RecyclingConcrete-FullReport.pdf](http://www.wbcscement.org/pdf/CSI-RecyclingConcrete-FullReport.pdf)]. World Bus. Counc. Sustain. Dev. Last Accessed:
- 11 2016.
- 12 **Weidema, B.P., Wesnaes, M.S., 1996. Data quality management for life cycle inventories**
- 13 **– an example of using data quality indicators. *Journal of Cleaner Production* 4(3–4):**
- 14 **167–174.**
- 15 Xiao, J., Wang, C.Q., Li, J., Tawana, M., 2012. Shake-table model tests on recycled aggregate
- 16 concrete frame structure. *ACI Struct. J.* 109, 777–786.
- 17 Yoo, S.W., Ryu, G.S., Choo, J.F., 2015. Evaluation of the effects of high-volume fly ash on
- 18 the flexural behavior of reinforced concrete beams. *Constr. Build. Mater.* 93, 1132–1144.
- 19 <https://doi.org/10.1016/j.conbuildmat.2015.05.021>
- 20 Yoon, S., Monteiro, P.J.M., Macpheec, D.E., Glasser, F.P., Imbabi, M.S.-E., 2014. Statistical
- 21 evaluation of the mechanical properties of high-volume class F fly ash concretes. *Constr.*
- 22 *Build. Mater.* 54, 431–442.
- 23 Zhao, J., Cai, G. and Yang, J., 2016. Bond-slip behavior and embedment length of
- 24 reinforcement in high volume fly ash concrete. *Materials and Structures.* Springer
- 25 Netherlands, 49(6) 2065–2082. doi: 10.1617/s11527-015-0634-2.

1 Zhang, Y., Junzhi Zhang, J., Luo, W., Jiandong Wang, J., Jiale Shi, J., Zhuang, H., Wang, Y.,  
2 2019. Effect of compressive strength and chloride diffusion on life cycle CO<sub>2</sub> assessment  
3 of concrete containing supplementary cementitious materials. J. Clean. Prod. 218, 450–  
4 458. <https://doi.org/10.1016/j.jclepro.2019.01.335>